

Greenhouse Cover

TAJO®

TAJO® LD Mulching-Soil Cover

Film usage	Soil cover
Width-meter	Up to 7
Thickness-Micron	15~50
Length	As required
Color	Black, Clear



Test items		Test Method	Units	Values
Tensile strength	MD	ASTM D882	MPa	28
	TD		MPa	29
Elongation	MD	ASTM D882	%	450
	TD		%	500
Tear resistance	MD	ASTM D1922	g/mm	9500
	TD		g/mm	18500
Drop dart impact	A method	ASTM D1709	g	350
Light transmission in PAR		ASTM D1003	%	Black -Opaque
Diffused light transmission in PAR			%	
Light transmission in IR			%	
Anti drip				-
Anti mist				-

Typical values



TAJO®
Greenhouse Cover Film

TAEKWANG NEWTEC Co., Ltd.

16, Seonyu-ro9-gagil, Yeongdeungpo-gu, Seoul, Korea **Tel** +82-2-3662-2367 **Fax** +82-2-3661-7513

Web site <http://www.plastar.co.kr> **Email** taekwang@plastar.co.kr